

Physical	Nominal Value Unit	Test Method
Density	1.10 g/cm ³	ISO 1183
Elastomers	Nominal Value Unit	Test Method
Tensile Stress ⁴ (Break)	2.00 MPa	ISO 37
Tensile Elongation ⁴ (Break)	600 %	ISO 37
Tear Strength ⁵	9.00 kN/m	ISO 34-1
Hardness	Nominal Value Unit	Test Method
Shore Hardness (Shore A)	30	ISO 7619
Flammability	Nominal Value Unit	Test Method
Flame Rating	HB	UL 94
Additional Information	Nominal Value Unit	Test Method
Adhesion to ABS - (A) ⁶	1.5 kN/m	VDI 2019
Adhesion to PC - (A) ⁶	1.5 kN/m	VDI 2019

**Thermoplastic
elastomer**