

# Aluminium Alloy 6082

## Alternative Designations

Standard	EN	ANSI/AA	UNS	AFNOR	SIS	UNE
Designation	EN- AW6082	AA6082	A96082	A- SGM0,7	4212	L- 3453

## Details

Typically formed by rolling and extrusion, this alloy has medium strength with very good weldability and thermal conductivity. It has high stress corrosion cracking resistance. It has a tensile strength that ranges from 140 – 330MPa. It is heavily employed in offshore construction and containers.

## Key Features

Good thermal conductivity • Good weldability • High stress corrosion cracking resistance

## Chemical Composition

Element	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	
Percentage	0.7 – 1.3	0.5	0.10	0.40 – 1.0	0.6 – 1.2	0.25	0.20	0.10	

## Mechanical Properties

Property	Yield strength [MPa]	Ultimate tensile strength [MPa]	Elongation [%]	Hardness
Value	110	205	14	65

## Physical Properties

Property	Value
Density [g/cm <sup>3</sup> ]	2.7
Module of elasticity [GPa]	70
Electrical conductivity [m/Ω · mm <sup>2</sup> ]	24 – 32
Coefficient of thermal expansion [K <sup>-1</sup> · 10 <sup>-6</sup> ]	23.4
Thermal conductivity [W/m · K]	170 – 220
Specific heat capacity [J/kg · K]	896