

Data Sheet: LDPE

(Low Density Polyethylene)

Details

This is the most flexible member of the polyethylene family. It offers good resistance to stress and pliability with good strength and toughness. It is lightweight and translucent. It is commonly used in food containers, toys, industrial parts and medical products.

Key Features

Flexible • Lightweight • Translucent • Resistant to stress

Thermal Properties

| Property | Value |
|---|-------|
| Heat deflection [°C] | 48 |
| Glass transition temperature [°C] | -110 |
| Vicat softening temperature [°C] | 89 |
| Coefficient of thermal expansion [K-1 · 10-6] | 100 |
| Thermal conductivity [W/m · K] | 0.33 |
| Specific heat capacity [J/kg · K] | 1900 |
| Melting point [°C] | 115 |

Mechanical Properties

| Property | Value |
|-----------------------------|-------|
| Tensile strength [MPa] | 10 |
| Modulus of elasticity [GPa] | 0.39 |
| Flexural strength [MPa] | 10.3 |
| Flexural modulus [GPa] | 0.199 |



| Hardness | 55 |
|-------------------------|-----|
| Elongation at break [%] | 100 |

Physical Properties

| Property | Value |
|---------------------------------|--------------------------|
| Density [g/cm³] | 0.918 |
| Water Absorption [%] | 0.005 |
| Electrical Resistivity [ohm-cm] | 0.917 × 10 ¹⁵ |

Reference

Datasheets provided by Xometry contain materials sourced through trusted OEMs, material distributors, and databases. Please visit Materialdatacenter.com for further information on this material.