

Manufacturing On Demand

Data Sheet: PBT(*Polybutylene terephthalate*)

Details

This material has excellent resistance to abrasion and creep. It has a low coefficient of friction and a low moisture absorption. PBT is chemically resistant to strong and weak acids. It is used in gears, bushings and bearings.

Key Features

Resistant to abrasion and creep • Low moisture absorption

Thermal Properties

| Property | Value |
|---|-------|
| Heat deflection [°C] | 160 |
| Glass transition temperature [°C] | 22 |
| Vicat softening temperature [°C] | 150 |
| Coefficient of thermal expansion [K-1 · 10-6] | 108 |
| Thermal conductivity [W/m · K] | 0.27 |
| Specific heat capacity [J/kg · K] | 1421 |
| Melting point [°C] | 223 |

Mechanical Properties

| Property | Value |
|-----------------------------|-------|
| Tensile strength [MPa] | 82.7 |
| Modulus of elasticity [GPa] | 4 |
| Flexural strength [MPa] | 80 |



Manufacturing On Demand

| Flexural modulus [GPa] | 3.83 |
|-------------------------|------|
| Hardness | 170 |
| Impact strength [KJ/m²] | 4 |
| Elongation at break [%] | 130 |

Physical Properties

| Property | Value |
|---------------------------------|---------------------|
| Density [g/cm³] | 1.52 |
| Water Absorption [%] | 0.1 |
| Electrical Resistivity [ohm-cm] | 14×10^{15} |

Reference

Datasheets provided by Xometry contain materials sourced through trusted OEMs, material distributors, and databases. Please visit <u>Materialdatacenter.com</u> for further information on this material.