

Data Sheet: PET

(Polyethylene terephthalate)

Details

This material has a melting point of about 270°C; hence, molding is done at a high temperature. It is a hard material with low moisture absorption. It has good resistance to chemicals as well as good strength and stiffness. It is used for production of capacitors, recording tapes, bottles and electrical components.

Key Features

Rigid • Flame retardant • Resistant to heat and creep

Thermal Properties

Property	Value
Heat deflection [°C]	80
Glass transition temperature [°C]	70
Vicat softening temperature [°C]	74
Coefficient of thermal expansion [K-1 · 10-6]	60
Thermal conductivity [W/m · K]	0.28
Specific heat capacity [J/kg · K]	1100
Melting point [°C]	255

Mechanical Properties

Property	Value
Tensile strength [MPa]	85
Modulus of elasticity [GPa]	3
Flexural strength [MPa]	80

Flexural modulus [GPa]	1
Hardness	170
Impact strength [KJ/m ²]	2
Elongation at break [%]	15

Physical Properties

Property	Value
Density [g/cm ³]	1.38
Water Absorption [%]	0.1
Electrical Resistivity [ohm-cm]	16×10^{15}

Reference

Datasheets provided by Xometry contain materials sourced through trusted OEMs, material distributors, and databases. Please visit [Materialdatacenter.com](https://www.materialdatacenter.com) for further information on this material.