

A380

Alternative Designations

Standard	EN	AFNOR	UNS
Designation	EN AC-46500	A-S9U3A-Y4	A13800

Details

The A380 Aluminium gives an excellent combination of machinability, heat transfer and easy casting together with other properties. The fluidity of this material is excellent. It has a good resistance to hot cracking and pressure tightness. The presence of silicon makes it a bit rough. This material is applied in a variety of products such as engine mounts, electrical equipment chassis, generators and even furniture.

Key Features

Excellent machinability • Easy casting • Hot cracking resistance

Chemical Composition

Element	Cu	Fe	Mg	Mn	Ni	Si	Sn	Zn	Al
Percentage	3-4	≤1.3	≤0.1	≤0.5	≤0.5	7.5-9.5	≤0.35	≤3	80.3-89.5

[Datasheet >](#)

Mechanical Properties

Property	Yield strength [MPa]	Ultimate tensile strength [MPa]	Elongation [%]	Hardness
Value	159	324	2.5	80

Physical Properties

Property	Value
Density [g/cm ³]	2.76
Module of elasticity [GPa]	71.0
Electrical conductivity (S/m)	1.56e+7
Coefficient of thermal expansion [K ⁻¹ · 10 ⁻⁶]	21.1
Thermal conductivity [W/m · K]	109
Specific heat capacity [J/kg · K]	963