



# ZA-2

## Alternative Designations

ASTM AC43A, ZnAl4Cu3

## Key Features

High Strength • Hardness •  
Machinability

## Description

Compared to the other members of the Zamak family of metals, Zamak 2 is the highest in terms of tensile strength, hardness and creep resistance. It gains strength and hardness after ageing for the long term. Some of its outstanding casting qualities are damping capacity and vibration attenuation. However, it gets brittle and shrinks with time. It is used in the production of short-run injection moulding dies.





## Datasheet &gt;

**Mechanical Properties**

Yield strength	283 MPa
Tensile strength	359 MPa
Elongation at break	7%
Hardness	100
Module of elasticity	85.5 GPa

**Chemical Composition**

Al	3.7 - 4.3%	N	-
Bi	-	Nb	-
C	-	Ni	-
Cd	0.003 - 0.004%	O	-
Co	-	P	-
Cr	-	Pb	0.004-0.005%
Cu	2.6 - 3.3%	S	-
Fe	0.05 - 0.035%	Si	-
H	-	Sn	0.0015-0.002%
Mg	0.02 - 0.06%	Ti	-
Mn	-	V	-
Mo	-	Zn	Rest is Zn

**Physical Properties**

Density	6.6 kg/dm <sup>3</sup>
Electrical conductivity	1.46+07 m/Ω • mm <sup>2</sup>
Coefficient of thermal expansion	27.7 K <sup>-1</sup> • 10 <sup>-6</sup>
Thermal conductivity	104 W/m • K
Specific heat capacity	419 J/kg • K

