

## 8100

### Description

The 8100 is a high-transparency and low-viscosity SLA photosensitive polymer suitable for stereolithography (SLA) 3D printing rapid prototyping systems with 355 nm light sources.



### Features

Features: High transparency, excellent strength and toughness, high precision and good dimensional stability

Color: Transparent

Note: The 8100 should not be used or stored at a higher temperature, specifically used at  $26\pm 2^{\circ}\text{C}$ , and stored at  $25\pm 5^{\circ}\text{C}$ .

Advantages: Parts made of 8100 can maintain stable characteristics for up to 6.5 months.

Recommended applications: Automotive, medical, consumer electronics, toys, displays, etc.

### Parameters

Technical Data - Liquid Properties		
Appearance	Nearly colorless transparent viscous liquid	
Viscosity	200mPa·s@25°C	
Density	~1.12 g/cm3@25°C	
TECHNICAL DATE-OPTICAL PROPERTITES		
Recommended Layer Thickness of Construction		0.1mm
Ec		11.8mJ/cm2
Penetration Depth		0.145mm
TECHNICAL DATE- MECHANICAL PROPERTITES		
Mechanical Properties		UV Postcure
Property Description	ASTM Method	Metric
Tensile Strength	D638M	48MPa
Elongation at Break	D638M	12%
Flexural Strength	D790M	86MPa
Flexural Modulus	D790M	2100MPa
Izod Impact- Notched	D256A	28j/m
Hardness- Shore D	D2240	82
Water Absorption	D570-98	0.48%